

A search for incipient lattice instabilities in MgB_2 by anelastic spectroscopy

F.Cordero,¹ R. Cantelli,² G. Giunchi,³ and S. Ceresara³

¹*CNR, Istituto di Acustica "O.M. Corbino", Via del Fosso del Cavaliere 100, I-00133 Roma, Italy and Unità INFN-Roma1, P.le A. Moro 2, I-00185 Roma, Italy*

²*Università di Roma "La Sapienza", Dipartimento di Fisica, and Unità INFN-Roma 1, P.le A. Moro 2, I-00185 Roma, Italy*

³*EDISON S.p.A, Foro Buonaparte 31, I-20121 Milano, Italy*

We measured the complex dynamic elastic modulus of MgB_2 between 1.3 and 650 K at frequencies included between 5 and 70 kHz. The main purpose of this work is to search for possible lattice instabilities, which could contribute to enhance the electron-phonon coupling. The Young's modulus indeed presents an anomalous softening on cooling below 400 K, and hysteresis between cooling and heating. Such anomalies, however, can be accounted for by intense relaxation processes with maxima between 50 and 150 K, whose nature is not yet clarified, and by geometric defects generated by the anisotropic thermal expansion between the grains during thermal cycling. Additional intense relaxation processes are observed above room temperature, and their possible origin is discussed. The influence of the highly anharmonic in-plane vibration modes of the B atoms on the elastic and anelastic properties of MgB_2 is discussed in detail.

The discovery of superconductivity with $T_c = 39$ K in MgB_2 is arousing great interest, since this intermetallic compound seems to be a simple BCS superconductor, without any of the other mechanisms for high- T_c superconductivity that are hypothesized for the cuprate superconductors. Electronic band calculations^{1,2} indicate a predominant hole conduction in the two-dimensional σ band from the sp_xp_y orbitals of B, with an extremely large deformation potential for the B bond stretching mode, which dominates the electron-phonon coupling. The most recent first principle calculations of the electronic bands and phonons² indicate that the zone-center optical mode with E_{2g} symmetry, involving vibrations of the B atoms within the ab plane, has very flat anharmonic potential, and can account for the observed T_c with a calculated electron-phonon coupling constant $\lambda \simeq 1$. An experimental indication of the anharmonicity of that mode comes from the high value of its Grüneisen parameter, evaluated from the shift of the corresponding Raman band with pressure.³ Still, it is important to ascertain whether there are other anharmonic or unstable modes that are not easily seen by phonon DOS measurements² and other spectroscopies, but can contribute to the large electron-phonon coupling. In many cases of BCS superconductivity with high T_c , the strongly anharmonic phonons causing the enhanced electron-phonon coupling also produce a structural instability, which in general profoundly affects the acoustic properties of the material. The best known examples are the A15 superconductors,⁴ where a clear correlation exists between the occurrence of a transformation from cubic to tetragonal, often assimilated to a martensitic transformation, and a high value of T_c . It should be emphasized that the occurrence and the entity of the structural instability in the A15 compounds is rather sensitive to the material preparation, and the easiest method for revealing it was the observation of softening of the elastic moduli on cooling below room temperature.⁴ Also the superconducting perovskite BKBO presents structural instabilities,^{5,6} while ultrasonic absorption peaks in BPBO are interpreted in terms of strong phonon anharmonicity.⁷

In the case of MgB_2 a possible unstable mode is the B_{1g} mode of the out-of plane vibrations of the B atoms, even though the first principle calculations indicate a stiff and harmonic mode.² In fact, it has been observed that MgB_2 is close to the condition of buckled B planes in a phase diagram of the AB_2 compounds versus charge density and B-B distance.⁸ In addition, when the hole density in the B planes is progressively reduced by partially substituting Mg with Al, the c lattice parameter collapses in correspondence with the disappearance of superconductivity, suggesting that MgB_2 is close to a structural instability at slightly higher electron density.⁹

The anelastic spectroscopy is very sensitive to structural instabilities, and therefore we measured the complex dynamic Young's modulus of MgB_2 between 1.3 and 650 K, searching for possible signs of lattice instabilities not yet detected by neutron diffraction^{2,10} and other

spectroscopies.

The sample was prepared by reacting Mg and B in a sealed stainless steel tube, lined with Nb foil, at 950 °C for 2 hours. Further preparative details are reported elsewhere.¹¹ A bar $39 \times 6 \times 1$ mm³ was cut by spark erosion. The mass density was $\rho = 2.27$ g/cm³, 86% of the theoretical one. The superconducting transition, measured by resistivity, was centered at 39.5 K, with a width of 1 K. The X-ray diffraction spectra showed the presence of a residual minority phase of metallic Mg, presumably at the grain boundaries. The sample was suspended with thin thermocouple wires and electrostatically excited on its flexural modes, whose resonant frequencies are given by $f_n = \alpha_n h / l^2 \sqrt{E' / \rho}$, where $E(\omega, T) = E' + iE''$ is the complex dynamic Young's modulus,¹² l and h the sample length and thickness, and α_n numerical constants depending on the vibration mode. The 1st, 3rd and 5th modes could be excited, at $\omega / 2\pi = 5.7, 38$ and 73 kHz respectively at 1 K. The value of the Young's modulus at room temperature, not corrected for the sample porosity and the Mg traces, is $E = 167$ GPa. The imaginary part is related to the elastic energy loss coefficient $Q^{-1} = E'' / E'$, which was measured from the width of the resonance curves.

Figure 1 shows the anelastic spectrum between 1 and 620 K, measured by exciting the first flexural mode. A first result is the absence of anomalous softening below 150 K, so excluding a scenario like that of the A15 compounds, where the strong phonon anharmonicity is due to a mode which becomes unstable slightly above T_c . Still, anomalous softening and hysteresis between cooling and heating are observed between 400 and 150 K. Such anomalies, however, should not be straightforwardly attributed to a structural instability, since microplastic phenomena connected with the anisotropic thermal expansion of the hexagonal crystallites are expected. Neutron diffraction¹⁰ experiments have shown a large anisotropy of the thermal expansion and compressibility, both being about twice larger along the c axis. These plastic phenomena have already been observed in other hexagonal polycrystals, like Zn, Co and Cd,¹³ whose thermal expansivity is sufficiently anisotropic and the critical stress σ_c for plastic deformation sufficiently low to yield the formation of dislocations during thermal cycling. The increase of the density of geometrical defects results in a reduction of the modulus, and the competition between the defect generation and annihilation, the latter especially at high temperature, explains the hysteresis between cooling and heating above 130 K. Below that temperature the thermal expansion becomes so small that the stress generated at the grain boundaries is below σ_c and no further modification in the geometrical defects occurs. We do not know what type of geometrical defects accommodates the strains generated during thermal cycling in MgB_2 , but they are not exclusively accommodated at the Mg impurities between the grains; in fact, after heating the sample up to 690 K in vacuum, about 8% of Mg was lost, the absorption component at

80 K was reduced, but the hysteresis of the modulus below room temperature was unchanged. Also the elastic energy loss is partially due to the motion of the geometrical defects, at least above 150 K, since it has a component which increases with the cooling/heating rate, and exhibits hysteresis, as shown by the open symbols in Fig. 1. The plastic phenomena can account for the irregularities and hysteresis of $E(T)$ between 150 and 400 K but probably not completely for the plateau of $E'(T)$ between these temperatures. This plateau could also have another origin; indeed, a small softening of some modes appears in the phonon DOS measured by neutron scattering² around 325 K. We shall see however, that also the relaxation processes observed below room temperature in the elastic energy loss might cause a similar effect.

The intense absorption peak at 475 K is due to a thermally activated relaxation process,¹² namely it can be described as a contribution $\delta E = -\Delta/(1 + i\omega\tau)$ to $E(\omega, T)$, where the relaxation time follows the Arrhenius law $\tau = \tau_0 \exp(W/T)$. The absorption peak and modulus dispersion of this type of processes shift to higher temperature with increasing frequency. Due to the high damping, the higher frequency modes could be followed only up to 440 K, but exhibited such a shift, and could be interpolated by the expression

$$\delta E = -\Delta/[1 + (i\omega\tau)^\alpha], \quad (1)$$

where the parameter $\alpha = 0.65$ reproduces the broadening of the spectrum of the energy barriers ($\alpha = 1$ in the monodispersive case), $W = 0.89$ eV and $\tau_0 = 10^{-14}$ s. The dotted lines in Fig. 1 are the corresponding contributions to the absorption and to E' , plus the tail of another process at higher temperature, probably connected with grain-boundary motion or with the loss of Mg. The value of τ_0 is typical of point defect motion, as could be the migration of Mg atoms and vacancies, but, due to the bad quality of the higher frequency data, we cannot exclude that τ_0 is actually longer and therefore connected with the motion of geometrical defects.

In view of the occurrence of plastic phenomena during thermal cycling above ~ 130 K, it is likely that the absorption contains an important contribution from the relaxation of extended lattice defects. Some contribution may also be expected from Mg at the grain boundaries, since deformed Mg presents an extremely broad absorption maximum¹⁴ reminiscent of the curves found here below room temperature; nevertheless, the contribution of metallic Mg is weighted with its molar fraction, i.e. few percents, and considering that the intensity of the peak in deformed Mg¹⁴ never exceeds 2×10^{-3} , it cannot account for elastic energy loss curves of Fig. 2. In addition, at T_c it is evident a change of the slope of both the imaginary and real parts of $E(T)$, which must be connected with processes occurring in the superconducting bulk of MgB₂. Another unusual feature of the anelastic spectrum below 200 K is that the curve simultaneously

measured at higher frequency, instead of being simply shifted to higher temperature, as for any thermally activated relaxation process, is about a factor 1.32 more intense than that at lower frequency. Finally, it should be noted that the spectrum below 100 K is perfectly reproducible during various cooling and heating cycles; considering the extreme sensitivity of the dislocation peaks to the sample state, and the occurrence of plastic phenomena during thermal cycling, it is unlikely that the low temperature spectrum is exclusively connected with geometrical defects.

It is tempting to relate the low temperature anelastic spectrum with the highly anharmonic E_{2g} optical mode which is thought responsible for the strong electron-phonon coupling. Indeed, a relaxation mechanism involving the soft optical modes responsible for the structural phase transformations in perovskites has been proposed by Barrett,¹⁵ and later adopted in order to explain the ultrasonic absorption in the perovskite superconductor⁷ BaPb_{1-x}Bi_xO₃ and even in some cuprate superconductors.¹⁶ The mechanism is analogous to the Akhiezer-type absorption,¹² but instead of the acoustic phonons, it is based on the existence of optical phonons with a large Grüneisen constant, $\gamma = -d(\ln\omega_0)/d\varepsilon$, namely whose frequency ω_0 strongly depends on a strain ε . The flexural vibration of the sample causes a non homogeneous uniaxial strain ε along the sample length and modulates the energies of the phonons according to their Grüneisen parameters. The phonons system goes out of thermal equilibrium if different modes have different values of γ , and the equilibrium is established with an effective phonon relaxation time τ_{eff} . The change of the population is reflected in the dynamic elastic modulus, which acquires an out of phase imaginary component and a temperature dependent softening. It is appropriate to discuss this mechanism, since the Grüneisen constant of the E_{2g} optical mode has been found to have a very large value at room temperature,³ $\gamma_{\text{op}} = \frac{1}{3} \frac{d \ln \nu}{d \ln a} \simeq 3.9$, a being the lattice constant, while normal values range between 1 and 2. Barrett solved the case in which the system is schematized with an optical mode with frequency ω_0 and large γ_{op} , and the acoustic modes with normal γ_{ac} ; since we are considering uniaxial strain $\varepsilon = da/a$ instead of volume change, we define $\bar{\gamma} = 3(\gamma_{\text{op}} - \gamma_{\text{ac}}) \simeq 7$, where $\gamma_{\text{ac}} \sim 1.5$ is assumed. The contribution of the phonon relaxation to the dynamic Young's modulus E is¹⁵

$$\delta E = -\frac{\bar{\gamma}^2}{v_0} T C_{\text{op}} \frac{1 + i\omega\tau_{\text{eff}}}{1 + (\omega\tau_{\text{eff}})^2} \quad (2)$$

$$\tau_{\text{eff}} = \tau_{\text{op}} + \frac{C_{\text{op}}}{C_{\text{ac}}} \tau_{\text{ac}} \quad (3)$$

where v_0 is the cell volume, C_{ac} and C_{op} are the specific heat of the acoustic and optic modes per molecule and τ_{ac} and τ_{op} are their relaxation times. The elastic energy loss coefficient is, for $\omega\tau_{\text{eff}} \ll 1$,

$$Q^{-1} = \frac{E''}{E'} = \frac{\bar{\gamma}^2}{v_0 E} T C_{\text{op}} \omega \tau_{\text{eff}} = \Delta(T) \omega \tau_{\text{eff}}; \quad (4)$$

where C_{op} has the usual expression $k_B [(\hbar\omega_0/2T)/\sinh(\hbar\omega_0/2T)]^2$ with³ $\hbar\omega_0/k_B = 830$ K, $E = 167$ GPa and $v_0 = 29 \times 10^{-24}$ cm³; the resulting relaxation strength Δ is 6.6×10^{-5} at 100 K and 6.5×10^{-3} at 300 K, but has to be multiplied by the factor $\omega \tau_{\text{eff}}$, which is very small. In fact, the phonon relaxation rates and therefore τ_{eff}^{-1} should exceed 10^{12} s⁻¹; τ_{ac} can be deduced from the lattice thermal conductivity κ through the collision formula $\kappa = \frac{1}{3} C_{\text{ac}} \bar{v}^2 \tau_{\text{ac}}$. Assuming $\kappa \simeq 0.1$ W/(cm K) found¹⁷ above 100 K, an average sound velocity somewhat lower than that deduced from $\sqrt{E/\rho} = 8 \times 10^5$ cm/s, and a Debye lattice specific heat, it results $\tau_{\text{ac}} < 10^{-12}$ s; τ_{op} can be assumed to be of the same order of magnitude or even smaller. Since our measuring frequency is only $\omega \sim 10^4 - 10^5$, the $\omega \tau_{\text{eff}}$ factor makes the imaginary part negligibly small, and therefore the absorption peaks around 100 K cannot be attributed to an Akhiezer type mechanism involving the anharmonic optic phonon. Still, the real part of δE contributes to the modulus softening with a substantial $\delta E/E = -\Delta(T)$; the continuous curve in Fig. 1 is calculated with the above parameters, assuming a temperature independent $\bar{\gamma} = 7$.

Although the mechanisms producing the acoustic absorption below 150 K remain unclear, it is worth checking whether they can also be the origin of the anomalous softening observed below 400 K. The imaginary part of the dynamic modulus should be describable in terms of a superposition of relaxation processes like Eq. (1), where the phenomenological parameter $\alpha \leq 1$ describes the broadening of the spectrum of relaxation times around an average value τ , and the relaxation strength is generally $\Delta \propto 1/T$ or nearly constant. In order to reproduce the experimental curves, we need a $\Delta(T)$ strongly increasing with temperature, and therefore we adopt $\Delta(T) \propto 1/[T \cosh^2(E/2T)]$, appropriate¹⁸ for relaxation occurring between states which differ in energy by E . The solid lines roughly interpolating the absorption data in Fig. 2 are obtained with the following parameters, $\tau = 5 \times 10^{-14} \exp(800/T)$ s, $\alpha = 0.2$, $E/k_B = 230$ K for the peak at 70-80 K, and $5 \times 10^{-15} \exp(2900/T)$ s, $\alpha = 0.4$, $E/k_B = 130$ K for the peak at 150 K. We do not attribute a particular meaning to these values, since it is possible that the two peaks are superimposed to a broader maximum, which has not been considered. The fit is therefore only indicative, but it shows that the anomalous softening below 400 K may be accounted for by the same relaxation processes which cause absorption at low temperature; in fact, the continuous line in the upper panel of Fig. 2 is the real part corresponding to the curves in the lower panel and even exceeds the experimental softening. The fact that the magnitude of the negative step of E' is much larger than the amplitude of the E'' peaks is a consequence of the non additivity of the amplitudes of the elementary peaks, whose maxima

occur at different temperatures.

The presence of these intense relaxation processes also masks the negative jump and positive change of the slope of the elastic moduli due to the superconducting transition;⁴ in fact, the latter are of the order of 10^{-4} or less, while the low temperature relaxation processes cause a modulus defect of the order of 10^{-3} at 40 K, and they are affected by the transition to the superconducting state, as observed in both the real and imaginary parts of E . In order to analyze the intrinsic changes of the moduli at T_c one should be able to subtract the relaxational contribution. For this reason, although we can see the expected jump and change of slope of $E'(T)$ below T_c , we omit the discussion of this issue.

In conclusion, we measured the complex dynamic elastic modulus of MgB₂ with the principal aim of searching for possible lattice instabilities, which might contribute to enhancing the electron-phonon coupling without being yet revealed by other spectroscopies. The Young's modulus indeed presents an anomalous plateau on cooling between 400 and 150 K, and hysteresis between cooling and heating. The softening, however, can be accounted for by intense relaxation processes with maxima between 50 and 150 K, whose nature is not yet clarified. The hysteresis is explainable in terms of generation and annihilation of geometric defects due to the stresses generated by the anisotropic thermal expansion between the grains during thermal cycling. The influence of the highly anharmonic vibration modes of the B atoms on the elastic and anelastic properties of MgB₂ is discussed in detail; such anharmonic phonons produce negligible acoustic absorption at the low frequencies of the present study, but they may substantially contribute to the total softening of the elastic modulus with increasing temperature.

Edison acknowledges the Lecco Laboratory of the CNR-TEMPE, Milano, Italy, for making available its facilities for materials preparation.

¹ J.M. An and W.E. Pickett, Phys. Rev. Lett. **86**, 4366 (2001).

² T. Yildirim *et al.*, cond-mat/0103469.

³ A.F. Goncharov *et al.*, cond-mat/0104042.

⁴ L.R. Testardi, *Physical Acoustics*, ed. by W.P. Mason and R.N. Thurston, p. 193 (Academic, New York, 1973).

⁵ S. Zherlitsyn *et al.*, Eur. Phys. J. B **16**, 59 (2000).

⁶ M. Braden *et al.*, Phys. Rev. B **62**, 6708 (2000).

⁷ S. Mase *et al.*, Solid State Commun. **57**, 227 (1987).

⁸ A. Bianconi *et al.*, cond-mat/0102410.

⁹ J.S. Slusky *et al.*, cond-mat/0102262.

¹⁰ J.D. Jorgensen *et al.*, cond-mat/0103069.

¹¹ Edison S.p.A patent pending.

¹² A.S. Nowick and B.S. Berry, *Anelastic Relaxation in Crystalline Solids*. (Academic Press, New York, 1972).

- ¹³ M.H. Youssef and P.G. Bordoni, *Phil. Mag. A* **67**, 883 (1993).
- ¹⁴ R.T.C. Tsui and H.S. Sack, *Acta metall.* **15**, 1715 (1967).
- ¹⁵ H.H. Barrett, *Physical Acoustics*. ed. by W.P. Mason and T.N. Thurston, p. 65 (Academic Press, New York, 1970).
- ¹⁶ Y. Horie *et al.*, *J. Phys. Soc. Jap.* **58**, 279 (1989).
- ¹⁷ E. Bauer *et al.*, cond-mat/0104203.
- ¹⁸ F. Cordero, *Phys. Rev. B* **47**, 7674 (1993).

FIG. 1. Real and imaginary parts of the anelastic spectrum of MgB_2 , measured exciting flexural vibrations at 5 kHz. The arrows and numbers indicate the order of the cooling and heating runs. The dotted lines in the lower and upper panel are a fit to the high temperature relaxation peaks and the corresponding modulus defect, respectively. The dashed line is the estimated softening from the anharmonic E_{2g} optic mode of the in-plane B vibrations, with the value of the Grüneisen parameter measured at room temperature. The gray curve is the experimental Young's modulus after subtraction of the above contributions.

FIG. 2. Real and imaginary parts of the anelastic spectrum of MgB_2 , measured exciting flexural vibrations at 5.7 kHz and 73 kHz during the same cooling run. The continuous lines in the lower panel are a fit assuming broad thermally activated relaxation processes with the parameters given in the text; the line in the upper panel is the corresponding contribution to the real part of the elastic modulus. The arrows indicate the superconducting T_c , at which the curves change the slope.



